

# Full declaration of ingredients

## Natural Oil Woodstain

### Binding agents:

- based on the re-growing vegetable raw materials sunflower oil, soybean oil, thistle oil and linseed oil

### Solvents:

- aliphatic hydrocarbons = disaromatized white spirit (benzene free)

### Pigments:

- mineral pigments on the basis of ore; titanium dioxide and iron oxides (yellow, red, brown, black)
- organic pigments (yellow, red, green, blue) which are in compliance with German Industrial Norm DIN 53 160 (fast to perspiration and saliva) and Euro Norm EN 71.3 (safety of children's toys)

### Earths:

- mineral origin, quartz sand, dolomite, spar and swelling clay (argillaceous rock)

The used mineral pigments and earths have been purified from all poisonous ingredients (e.g. heavy metals) and are physiologically safe.

### Additives:

- zinc-zirconium-cobalt-octoates (are obtained from the respective minerals and are lead-free)
- ketoximes
- polysiloxanes (on the basis of silicic acid)

The listed ingredients serve to a regular drying and the prevention of film formation (5 years storage stability) as well as a strong water repellency.

### Active agents (film protection):

- Dichlofluanid

Osmo Natural Oil Woodstain contains active agents to protect the coating against algae and fungus attack.

According to EG requirements Osmo Natural Oil Woodstain does not have to be marked. Further details concerning technical characteristics etc. can be obtained from the respective product information.

*(Dated 07/2010)*